

## Product Information

[www.polymett.com](http://www.polymett.com)

### General Description

CAS No. 25038-59-9

Featuring nonpoisonous, odourless, tasteless, and excellent transparency, high strength, perfect processability, our Polyester Chip has been widely used by a plenty of overseas customers, and becomes preferred material in the fields of water bottles, soft drink bottles, non-beverage bottles, and PET sheets.

### Main Applications

PET CZ-302 is for packing bottles, like pure water, natural mineral water, distilled water, drinking water.

PET CZ-318 is for small-package edible oil bottles, liquor bottles, medicine bottles, cosmetics bottles, PET sheets.

PET CZ-333 is for hot-filling bottles, like tea drinks, fruit-juice drinks and other medium type drinks.

PET CZ-328 is for carbonated drinks bottles and 3-gallon, 5 gallon big bottles.

PET CZ-5022 is for making the terylene filament & terylene staple fiber, PET industry film and etc.

### Packaging

1.05 MT per jumbo bag, 20 bags in one 20' FCL

### Technical Data Sheet

Parameter	Unit	Grade				
		PET CZ-302	PET CZ-318	PET CZ-333	PET CZ-328	PET CZ-5022
I.V.	dL/g	0.80 ± 0.02	0.83 ± 0.02	0.80 ± 0.02	0.85 ± 0.02	0.64 ± 0.015
Crystallinity	%	≤ 60	≤ 60	≤ 60	≤ 60	--
Content of COOH	mol/t	≤ 26	≤ 26	≤ 26	≤ 26	≤ 30
Content of acetaldehyde	ppm	≤ 1.0	≤ 1.0	≤ 1.0	≤ 1.0	--
Color value	L	--	≥ 83	≥ 83	≥ 82	≥ 75
	B	--	≤ 1.0	≤ 1.0	≤ 1.0	4.0 ± 2.0
Dust content	ppm	≤ 100	≤ 100	≤ 100	≤ 100	30
Melting point	°C	243 ± 2	243 ± 2	250 ± 2	243 ± 2	259 ± 2
Wt. of 100 chips %	g	1.55 ± 0.10	1.55 ± 0.10	1.55 ± 0.10	1.55 ± 0.10	--
Water content	wt%	≤ 0.2	≤ 0.2	≤ 0.2	≤ 0.2	≤ 0.4

Series no.:  
Data Updated:

PCL2009-25038599  
December 1, 2009

IMPORTANT! Although POLYMET believes that the information contained herein is accurate as of date hereof, POLYMET makes neither warranty nor guarantee, expressed or implied, that the result described herein will be obtained under end-use conditions. Each user bears full responsibilities for making its own determination and must identify and perform all tests and analyses necessary to assure that its finished parts incorporating POLYMET material or products will be safe and suitable for use under end-use conditions. Keep the directions and advices contained in MSDS (Material Safety Data Sheet) when handling the product and work out proper safety countermeasures. The substance described in MSDS is intended for general condition and each user must work out additional safety countermeasures when mixing with other products or using in special condition. POLYMET reserves the right to make any amendment without prior notice.

