

Technical Data Sheet

HIPS(High Impact Poly Styrene)

HI 425EH

Features	Cold resistance extrusion
Applications	Disposable cups, Food packing sheet, Wrapping films, Trays, Washing machines

Physical	Test Method	Value
Density	ASTM D792	1.03 g/cm ³
Melt Flow Index (200°C, 5kg)	ASTM D1238	4.5 g/10min
Mold Shrinkage	ASTM D955	0.3 ~ 0.6 %
Water absorption	ASTM D570	0.03 %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	240 kg/cm ² (3,408) (psi)
Elongation	ASTM D638	60 %
Flexural Strength	ASTM D790	300 kg/cm ² (4,260) (psi)
Flexural Modulus	ASTM D790	17,500 kg/cm ² (248,500) (psi)
Izod Impact Strength(3.2mm)	ASTM D256	9.5 kgcm/cm (1.76) (ft-lb/in)
Rockwell Hardness(L scale)	ASTM D785	60

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	74 °C (165) (°F)
Vicat Softening Temperature(1kg, 50°C/h)	ASTM D1525	95 °C (203) (°F)

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.

Technical Data Sheet

HIPS(High Impact Poly Styrene)

HI 425EH

Processing guide

Injection Guide	Unit	Value
Nozzle	°C	190~220
Front	°C	190~210
Middle	°C	180~200
Rear	°C	170~190
Hopper Throat	°C	45
Mold	°C	40~60

Extrusion Guide	Unit	Value
Zone 1	°C	170~190
Zone 2	°C	180~200
Zone 3	°C	180~210
Zone 4	°C	190~220
Zone 5	°C	200~220
Screen Changer	°C	190~210
Adaptor	°C	200
Die	°C	190~210

Drying	Unit	Value
Temperature	°C	60~70
Time	hr	1~3

Notes

These are only mentioned as general guidelines.