

**Samsung Cheil Industries Starex<sup>®</sup> CR-0760 ABS, Unreinforced**

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

**Material Notes:**

Good chemical resistance Information provided by Samsung Cheil Industries.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Samsung-Cheil-Industries-Starex-CR-0760-ABS-Unreinforced.php](http://www.lookpolymers.com/polymer_Samsung-Cheil-Industries-Starex-CR-0760-ABS-Unreinforced.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	3.7 g/10 min	3.7 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 Å°C	@Load 11.0 lb, Temperature 392 Å°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength, Yield	41.2 MPa	5970 psi	5 mm/min; ASTM D638
Flexural Strength	57.9 MPa	8400 psi	2.8 mm/min; ASTM D790
Flexural Modulus	1.96 GPa	284 ksi	2.8 mm/min; ASTM D790
Izod Impact, Notched	1.77 J/cm	3.31 ft-lb/in	ASTM D256
	@Thickness 6.35 mm	@Thickness 0.250 in	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	95.0 Å°C	203 Å°F	B/50; ISO R306

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China