

ER459

Injection Molding Grade

Description

- Medium Heat Resistance

Applications

- Automotive, Electric / Electronic Products

Properties	Method	Unit	ER459
Physical			
Specific Gravity , 23°C	ISO 1183		1.05
Mold Shrinkage , 23°C, 3.2mm , 23°C	ISO 294-4	%	0.4 ~ 0.7
Melt Volume Rate , 220°C, 10kg	ISO 1133	cm ³ /10min	16
Mechanical			
Tensile Strength at Yield , 23°C, 50mm/min, 4mm	ISO 527	MPa	50
Tensile Elongation at Yield , 23°C, 50mm/min, 4mm	ISO 527	%, (Min)	5
Tensile Elongation at Break , 23°C, 50mm/min, 4mm	ISO 527	%, (Min)	10
Tensile Modulus , 23°C, 1mm/min, 4mm	ISO 527	MPa	2350
Flexural Strength , 23°C, 2mm/min, 4mm	ISO 178	MPa	75
Flexural Modulus , 23°C, 2mm/min, 4mm	ISO 178	MPa	2400
Izod Impact Strength , Notched, 4mm, 23°C	ISO 180/1A	kJ/m ²	20
Izod Impact Strength , Notched, 4mm, -30°C	ISO 180/1A	kJ/m ²	7
Charpy Impact Strength , 4mm, 23°C	ISO 179/1eA	kJ/m ²	20
Charpy Impact Strength , 4mm, -30°C	ISO 179/1eA	kJ/m ²	7
Rockwell Hardness , R-Scale	ISO 2039		107
Thermal			
HDT , Flatwise, 1.8MPa, 4mm, Unannealed	ISO 75	°C	84
HDT , Flatwise, 0.45MPa, 4mm, Unannealed	ISO 75	°C	91
HDT , Flatwise, 1.8MPa, 4mm, Annealed	ISO 75	°C	92
HDT , Flatwise, 0.45MPa, 4mm, Annealed	ISO 75	°C	96
VICAT , 50N, 50°C/h	ISO 306	°C	102

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date : 10-Nov-17 Issued Date : 2-Apr-20

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

ER459

Injection Molding Grade

Description

- Medium Heat Resistance

Applications

- Automotive, Electric / Electronic Products

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	2 ~ 4
Melt Temperature	°C	210 ~ 240
Nozzle Temperature	°C	200 ~ 230
Mold Temperature	°C	40 ~ 70
Back Pressure, Hydraulic Type	kg/cm ²	5 ~ 15
Screw Speed	rpm	30 ~ 60

Note

Back Pressure & Measuring Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.



Updated Date : 10-Nov-17 Issued Date : 2-Apr-20

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.