# **QAMAR FD21HN**

Linear Low Density Polyethylene SPDC Ltd.



#### Technical Data

### **Product Description**

QAMAR FD21HN is a Linear Low Density Polyethylene material. It is available in Africa & Middle East, Asia Pacific, Europe, or North America for blown film.

Important attributes of QAMAR FD21HN are:

- Antiblock
- Clarity
- Slip

#### Typical application of QAMAR FD21HN: Film

General			
Material Status	<ul> <li>Commercial: Active</li> </ul>		
Literature <sup>1</sup>	<ul> <li>Technical Datasheet (Eng</li> </ul>	ish)	
Availability	<ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul>	<ul><li>Europe</li><li>North America</li></ul>	
Additive	<ul> <li>Antiblock</li> </ul>	• Slip	
Features	<ul><li>Antiblocking</li><li>General Purpose</li></ul>	<ul><li>Medium Clarity</li><li>Slip</li></ul>	
Uses	• Film	General Purpose	
Processing Method	Blown Film		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.918 g/cm <sup>3</sup>	0.918 g/cm <sup>3</sup>	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0 g/10 min	2.0 g/10 min	ISO 1872-2
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	1310 psi	9.00 MPa	ISO 1872-2
Tensile Strain (Break)	> 430 %	> 430 %	ISO 1872-2
Flexural Modulus	29000 psi	200 MPa	ISO 1872-2
Films	Nominal Value (English)	Nominal Value (SI)	Test Method
Film Thickness - Tested	1.2 mil	30 µm	
Tensile Modulus			ISO 527-3
MD : 1.2 mil (30 μm)	27600 psi	190 MPa	
TD: 1.2 mil (30 µm)	30500 psi	210 MPa	
Tensile Stress			ISO 527-3
MD : Break, 1.2 mil (30 μm)	5800 psi	40.0 MPa	
TD : Break, 1.2 mil (30 µm)	5080 psi	35.0 MPa	
Tensile Elongation			ISO 527-3
MD : Break, 1.2 mil (30 μm)	600 %	600 %	
TD : Break, 1.2 mil (30 µm)	900 %	900 %	
Dart Drop Impact (1.2 mil (30 µm))	110 g	110 g	ISO 7765-1
Elmendorf Tear Strength			ISO 6383-2
MD : 1.2 mil (30 μm)	6.7 lbf	30 N	
TD: 1.2 mil (30 µm)	31 lbf	140 N	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Shore Hardness (Shore D)	54	54	ISO 868
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Brittleness Temperature	< -94.0 °F	< -70.0 °C	ISO 974
Vicat Softening Temperature	212 °F	100 °C	ISO 306
Melting Temperature	252 °F	122 °C	ISO 11357-3
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Haze (1.18 mil (30.0 μm))	14 %	14 %	ISO 14782

Form No. TDS-112615-en

## **QAMAR FD21HN**

Linear Low Density Polyethylene SPDC Ltd.



www.ulprospector.com

Extrusion	Nominal Value (English)	Nominal Value (SI)	
Screw L/D Ratio	24.0:1.0	24.0:1.0	
E C 1 NO			

**Extrusion Notes** 

Resin Temperature: 180°C Blow Up Ratio: 2.0 Extruder: 40mm, L/D=24 Die Diameter: 75 mm

#### **Notes**

<sup>&</sup>lt;sup>1</sup> These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

<sup>&</sup>lt;sup>2</sup> Typical properties: these are not to be construed as specifications.

## **QAMAR FD21HN**

Linear Low Density Polyethylene SPDC Ltd.



Where to Buy

Supplier

SPDC Ltd.

, Japan Web: http://www.spdc.co.jp/

Distributor

Please contact the supplier to find a distributor for QAMAR FD21HN



Form No. TDS-112615-en