

## Kingfa FRHIPS-980 Flame Retardant Polystyrene

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

### Material Notes:

Features:UL 94 V-0 @ 1.6mm, V-0 @ 3.2mmExcellent balance properties, Non-DPOExcellent heat stability & electrical propertyColor tailor-made for clientApplications:Injection moldingGas assistant moldingTV, printer, photocopier and fax housingElectric and electronic cabinetInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kingfa-FRHIPS-980-Flame-Retardant-Polystyrene.php](http://www.lookpolymers.com/polymer_Kingfa-FRHIPS-980-Flame-Retardant-Polystyrene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 Å°C	@Load 11.0 lb, Temperature 392 Å°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.0 MPa	3480 psi	50mm/min; ASTM D638
Elongation at Break	40 %	40 %	50mm/min; ASTM D638
Flexural Strength	39.0 MPa	5660 psi	2mm/min; ASTM D790
Flexural Modulus	2.20 GPa	319 ksi	2mm/min; ASTM D790
Izod Impact, Notched	1.25 J/cm	2.34 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Å°C	@Thickness 0.126 in, Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
Hot Ball Pressure Test	85.0 Å°C	185 Å°F	IEC695-10-2
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Deflection Temperature at 1.8 MPa (264 psi)	75.0 Å°C	167 Å°F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Flammability, UL94	V-0	V-0	

Thermal Properties	@Thickness 1.60 mm Metric	@Thickness 0.0630 in English	Comments
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	<= 250 Å°C	<= 482 Å°F	
Rear Barrel Temperature	182 - 205 Å°C	360 - 401 Å°F	Start Point: 190Å°C
Middle Barrel Temperature	205 - 230 Å°C	401 - 446 Å°F	Start Point: 215Å°C
Front Barrel Temperature	215 - 240 Å°C	419 - 464 Å°F	Start Point: 225Å°C
Melt Temperature	220 - 245 Å°C	428 - 473 Å°F	Start Point: 230Å°C
Mold Temperature	30.0 - 60.0 Å°C	86.0 - 140 Å°F	Start Point: 50Å°C
Drying Temperature	70.0 Å°C @Time 7200 sec	158 Å°F @Time 2.00 hour	Pre-dry
Back Pressure	5.00 - 15.0 MPa	725 - 2180 psi	

Descriptive Properties	Value	Comments
Injection Speed	Slow to Moderate	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China