

Technical Data Sheet

EPS(Expandable Polystyrene)

EPS GN20

Features	General
Applications	Packing materials, Box,

Typical Properties	Test Method	Value
Bead Size	Kumho	0.6 ~ 0.9 mm
Expandability ¹⁾	Kumho	70 multiple
Blowing Agent	Kumho	5.0 %
Normal Molded Density Range	Kumho	17 ~ 20 kg/m ³

1) Expandability : Expansion multiple after 5 minutes in steam chamber (0.3 kgf/cm² steam pressure)

Mechanical Properties	Test Method	Value
Density	Kumho	20 kg/m ³
Flexural Demolition Load	Kumho	27 N
Compression Strength	Kumho	10 N/cm ²
Amount of Water Absorption	Kumho	0.3g /100cm ²

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.

STAVIAN[®]
CHEMICAL