

## Technical Data Sheet

### EPS(Expandable Polystyrene)

### EPS GN20 HC

**Features** General, High productivity(GN20 HC is 50% faster than the GN20)

**Applications** Packing materials, Box,

Typical Properties	Test Method	Value
Bead Size	Kumho	0.6 ~ 0.9 mm
Expandability <sup>1)</sup>	Kumho	70 multiple
Blowing Agent	Kumho	5.0 %
Normal Molded Density Range	Kumho	20 ~ 25 kg/m <sup>3</sup>

1) Expandability : Expansion multiple after 5 minutes in steam chamber (0.3 kgf/cm<sup>2</sup> steam pressure)

Mechanical Properties	Test Method	Value
Density	Kumho	20 kg/m <sup>3</sup>
Flexural Demolition Load	Kumho	26 N
Compression Strength	Kumho	9 N/cm <sup>2</sup>
Amount of Water Absorption	Kumho	0.4g /100cm <sup>2</sup>

#### Notes

These are just typical properties, not specifications. Users should confirm results by their own test.

STAVIAN<sup>®</sup>  
CHEMICAL