



## Data Sheet

[> Print](#)

<b>Classification</b>	Injection	HomoPolymer
<b>GRADE</b>	H550	

<b>Properties</b>	High Stiffness, Good Heat Resistance
<b>Application</b>	General Articles

## Data Sheet of Properties

Properties	ASTM	Unit	Standard Values
MI	D1238	g/10min	11.0
Density	D792	g/cc	0.903
Tensile Strength (Yield)	D638	kg/cm <sup>2</sup>	380
Elongation (Yield)	D638	%	10
Elongation (Break)	D638	%	>500
Flexural Modulus	D790A	kg/cm <sup>2</sup> (×1,000)	16
Rockwell Hardness	D785	R scale	105
IZOD Impact Strength	D256	kg.cm/cm	2.5
Vicat Softening Point	D1525B	°C	152
Heat Distortion Temp	D648	°C	125
Mold Shinkage (MD/TD)	D955	%	1.5~1.9
UL Rank	-	-	94HB
Haze	D1003	%	
Coefficient of Friction	D1894	-	
Young's Modulus	D882	kg/cm <sup>2</sup> (×1,000)	
Heat Sealing Temp	LG-Caltex	°C	

- The figures indicated on the table are standard values.
- The products can be designed as the applications and characteristics, please contact bellowing number.

**PP Planning & Export Team**

Jang, Hoon : hj4358@gscaltex.co.kr

Hong, Eui Gwang : C13138@gscaltex.co.kr

Kim, Chun Kyoung : C15746@gscaltex.co.kr

> Close

