



TECHNICAL DATA SHEET

HD T9

HD T9 is a HDPE stretched tape / raffia grade produced by Spherilene Technology

This grade can be used for stretched tape / raffia for woven fabrics & tarpaulin

HD T9 is characterized by excellent processability and mechanical strength

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg, 190°C)	ASTM D1238	g/10 min	1.1
Density (23°C)	ASTM D1505	g/cm ³	0.950
Physical Property			
Tensile Strength at Yield		MPa	26
Tensile Strength at Break	ASTM D638 (50 mm/min)	MPa	38
Elongation at Break		%	>1000
Notched Izod Impact Strength (23°C)	ASTM D256A	J/m	400
Flexural Modulus	ASTM D790A	MPa	1200
Hardness	ASTM D2240	Shore D	61
DSC Melting Temperature	ASTM D3418	°C	131
Suggested Processing Conditions			
Barrel Temperature		°C	200 – 240
Die Temperature	MICAI	°C	230 – 250
Quench Temperature		°C	30

^{*} Halene H is the registered trademark of High Density Polyethylene of HPL Mechanical Properties are on specimens from Compression Molded sheets

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request. Visit us at www.haldiapetrochemicals.com