



hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE

**Linear Low Density Polyethylene**

**HF1810X**

**Technical support:**  
 Sasol Chemicals  
 North America LLC  
 12120 Wickchester Lane  
 Houston, TX 77079

Email:  
 PolymersTechnical@us.sasol.com

**Sales office:**  
 Sasol Chemicals  
 North America LLC  
 12120 Wickchester Lane  
 Houston, TX 77079  
 Telephone: (281) 588 3000  
 Email:  
 PolymersSales@us.sasol.com

Date of issue: February 21, 2019

www.sasol.com

**Melt Index: 1.0 g/10min**

**Density: 0.918 g/cm<sup>3</sup>**

**Features**

- LLDPE Hexene copolymer
- Outstanding mechanical properties and processability
- Good heat sealing range

**Applications**

- General purpose packaging
- Heavy duty bags and high speed thin films
- Blown stretch film
- Blending into LDPE

**Additives**

- Antioxidant
- TNPP Free

Typical properties (not to be construed as specifications)		Value (English)	Value (SI)	Method
<b>Resin Properties</b>	Melt Index (190°C/2.16kg)	1.0 g/10min	1.0 g/10min	ASTM D1238
	Density	0.918 g/cm <sup>3</sup>	0.918 g/cm <sup>3</sup>	ASTM D792
	Base Density <sup>(1)</sup>	0.918 g/cm <sup>3</sup>	0.918 g/cm <sup>3</sup>	Sasol Method
<b>Film Properties</b>	Tensile strength at yield MD	2330 psi	16.0 MPa	ASTM D882
	Tensile strength at yield TD	2240 psi	15.4MPa	ASTM D882
	Tensile strength at break MD	8800 psi	60.7 MPa	ASTM D882
	Tensile strength at break TD	6990 psi	48.2 MPa	ASTM D882
	Tensile Elongation at break MD	580 %	580 %	ASTM D882
	Tensile Elongation at break TD	800 %	800 %	ASTM D882
	1% Secant Modulus MD	38000 psi	262 MPa	ASTM D882
	1% Secant Modulus TD	37000 psi	255 MPa	ASTM D882
	Elmendorf Tear Strength MD	380 g/mil	380 g/25.4 µm	ASTM D1922
	Elmendorf Tear Strength TD	850 g/mil	850 g/25.4 µm	ASTM D1922
	Dart Drop Impact Strength (F <sub>50</sub> )	120 g/mil	120 g/25.4 µm	ASTM D1709A
	Haze	12%	12%	ASTM D1003
Gloss (45°)	50%	50%	ASTM D2457	

(1) Base density is calculated assuming that the product doesn't contain any antiblock additive.

The above values were measured on a 0.8 mil (20 µm) film produced on a 2.5 in (63.5 mm) blown film extruder, using 448°F (231°C) melt temperature, with a 2.5:1 BUR, a die diameter of 6 in and a die gap of 70 mil (1.8 mm).

hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE

## Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

## Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

## Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

## Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.



STAVIAN®  
CHEMICAL

This publication contains information provided in good faith and is indicative, based on Sasol's current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased or supplied by Sasol Chemicals are subject to the terms and conditions set out in the contract, order confirmation and/or bill of lading. All data herein not to be construed as specifications.