

# HF380I

Injection Molding Grade

## Description

- High Flow, Paintable

## Applications

- Painting Products, Miscellaneous Goods

Properties	Method	Unit	HF380I
<b>Physical</b>			
Specific Gravity , 23°C	ASTM D792		1.04
Mold Shrinkage , 23°C, 3.2mm , 23°C	ASTM D955	%	0.4 ~ 0.7
Melt Flow Rate , 220°C, 10kg	ASTM D1238	g/10min	38
<b>Mechanical</b>			
Tensile Strength at Yield , 23°C, 50mm/min, 3.2mm	ASTM D638	MPa	43
Tensile Elongation at Yield , 23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	5
Tensile Elongation at Break , 23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	10
Tensile Modulus , 23°C, 50mm/min, 3.2mm	ASTM D638	MPa	2100
Flexural Strength , 23°C, 15mm/min, 3.2mm	ASTM D790	MPa	70
Flexural Modulus , 23°C, 15mm/min, 3.2mm	ASTM D790	MPa	2400
Izod Impact Strength , Notched, 3.2mm, 23°C	ASTM D256	J/m	270
Izod Impact Strength , Notched, 3.2mm, -30°C	ASTM D256	J/m	110
Izod Impact Strength , Notched, 6.4mm, 23°C	ASTM D256	J/m	270
Izod Impact Strength , Notched, 6.4mm, -30°C	ASTM D256	J/m	110
Rockwell Hardness , R-Scale	ASTM D785		106
<b>Thermal</b>			
HDT , Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	85
VICAT , 50N, 50°C/h	ASTM D1525	°C	93
RTI Electrical	UL 746B	°C	60
RTI Mechanical with Impact	UL 746B	°C	60
RTI Mechanical without Impact	UL 746B	°C	60
Flammability, 1.5mm	UL 94		HB
Flammability, 3.0mm	UL 94		HB

## Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date : 17-Nov-17 Issued Date : 20-Nov-20

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

# HF380I

Injection Molding Grade

## Description

- High Flow, Paintable

## Applications

- Painting Products, Miscellaneous Goods

## Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	2 ~ 4
Moisture Content	%	0.01 ~
Melt Temperature	°C	210 ~ 240
Nozzle Temperature	°C	200 ~ 250
Mold Temperature	°C	40 ~ 80
Back Pressure, Hydraulic Type	kg/cm <sup>2</sup>	5 ~ 15
Screw Speed	rpm	30 ~ 60

## Note

Back Pressure & Measuring Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

STAVIAN<sup>®</sup>  
CHEMICAL