

**PHYSICAL PROPERTIES OF STAREX ABS HG-0760**

Properties at 23°C	Test Method	Test Condition	Unit	Value
<b>Physical Properties</b>				
Specific Gravity	ASTM D792	Ivory Color	g/cm <sup>3</sup>	1.06
Water absorption	ASTM D570	24hr,immersion in water	%	0.3
Melt Flow Index	ASTM D1238	200°C/5Kg	g/10min	2.6
		220°C/10Kg	g/10min	25.0
		230°C/3.8Kg	g/10min	10.0
Mold Shrinkage	ASTM D955		%	0.5
Gloss	ASTM D523		%	96
<b>Mechanical Properties</b>				
Tensile Strength	ASTM D638	5mm/min	MPa (psi)	48 (6,830)
Elongation at Break	ASTM D638	5mm/min	%	37
Flexural Strength	ASTM D790	2.8mm/min	MPa (psi)	67 (9,530)
Flexural Modulus	ASTM D790	2.8mm/min	MPa (psi)	2,260 (321,000)
Izod Impact Strength (notched)	ASTM D256	1/4 inch	kg.cm/cm	19
		1/8 inch	kg.cm/cm	30
Rockwell Hardness	ASTM D785	R-scale	-	106
<b>Thermal Properties</b>				
Heat Deflection Temperature (unannealed),1/4"	ASTM D648	18.56Kg/cm <sup>2</sup>	°C	85
		4.6Kg/cm <sup>2</sup>	°C	95
Vicat Softening Temperature (unannealed)	ASTM D1525	5Kg/cm <sup>2</sup>	°C	96
		1Kg/cm <sup>2</sup>	°C	105
<b>Flammability</b>				
UL 94 Classification	UL94	1.5mm specimen	Recognized	HB
		3.0mm specimen	Recognized	HB
		6.0mm specimen	Recognized	HB
UV Resistance	ASTM D4459	300Hr Ivory color	Delta E	

\* The above values are only the representatives of natural color specimen, not supplementary.

\* Last revised ; 99/28/10