

RANPELEN J-560S

PP RANDOM COPOLYMER

General Information

Description

J-560S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers super excellent transparency, good stiffness/impact strength balance, high gloss, high hinge property and low smell.

Applications

- ◆ Cosmetics container & cap, Food container, Transparency case, Stationery
- ◆ Disposable syringe, CD/DVD case

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	18	g/10min		
Density	ASTM D792	0.9	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	300	kgf/cm ²	29	MPa
Tensile Strain (Break)	ASTM D638	>100	%	>100	%
Flexural Modulus	ASTM D790	12,000	kgf/cm ²	1,180	MPa
Rockwell Hardness	ASTM D785	95	R		
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	5.5	kgf·cm/cm	54	J/m
Notched Izod Impact Strength (-10℃)	ASTM D256	3.0	kgf·cm/cm	29	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	95	℃		
Additional Properties					
Haze	ASTM D1003	20	%		

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com

RANPELEN J-560S

PP RANDOM COPOLYMER

General Information

Description

J-560S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers super excellent transparency, good stiffness/impact strength balance, high gloss, high hinge property and low smell.

Applications

- ◆ Cosmetics container & cap, Food container, Transparency case, Stationery
- ◆ Disposable syringe, CD/DVD case

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ISO 1133	18	g/10min		
Density	ISO 1183	0.9	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ISO 527-1	270	kgf/cm ²	26	MPa
Tensile Strain (Break)	ISO 527-1	>100	%	>100	%
Flexural Modulus	ISO 178	9,900	kgf/cm ²	970	MPa

Impact

Notched Izod Impact Strength (23℃)	ISO 180	5.0	kgf·cm/cm	49	J/m
Notched Izod Impact Strength (-10℃)	ISO 180	2.5	kgf·cm/cm	24	J/m

Thermal

Heat Deflection Temperature (4.6kgf/cm ²)	ISO 75-1	85	℃		
---	----------	----	---	--	--

Additional Properties

Haze		20	%		
------	--	----	---	--	--

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com