

RANPELEN J-570S

PP RANDOM COPOLYMER

General Information

Description

J-570S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers high transparency, good stiffness/impact strength balance, high gloss, good flow and low smell.

Applications

- ◆ Food container, Stationery, Disposable syringe, CD/DVD case
- ◆ High transparency TWIM parts

Physical Properties¹

| Physical | Test Method | Nominal Values | | | |
|---|-------------|----------------|---------------------|-------|-----|
| Melt Flow Index | ASTM D1238 | 28 | g/10min | | |
| Density | ASTM D792 | 0.9 | g/cm ³ | | |
| Mechanical | | | | | |
| Tensile Stress (Yield) | ASTM D638 | 300 | kgf/cm ² | 29 | MPa |
| Tensile Strain (Break) | ASTM D638 | >100 | % | >100 | % |
| Flexural Modulus | ASTM D790 | 12,000 | kgf/cm ² | 1,180 | MPa |
| Rockwell Hardness | ASTM D785 | 95 | R | | |
| Impact | | | | | |
| Notched Izod Impact Strength (23 °C) | ASTM D256 | 4.5 | kgf·cm/cm | 44 | J/m |
| Notched Izod Impact Strength (-10 °C) | ASTM D256 | 3.0 | kgf·cm/cm | 29 | J/m |
| Thermal | | | | | |
| Heat Deflection Temperature (4.6kgf/cm ²) | ASTM D648 | 95 | °C | | |
| Additional Properties | | | | | |
| Haze | ASTM D1003 | 25 | % | | |

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com

RANPELEN J-570S

PP RANDOM COPOLYMER

General Information

Description

J-570S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers high transparency, good stiffness/impact strength balance, high gloss, good flow and low smell.

Applications

- ◆ Food container, Stationery, Disposable syringe, CD/DVD case
- ◆ High transparency TWIM parts

Physical Properties¹

| Physical | Test Method | Nominal Values | | | |
|---|-------------|----------------|---------------------|------|-----|
| Melt Flow Index | ISO 1133 | 28 | g/10min | | |
| Density | ISO 1183 | 0.9 | g/cm ³ | | |
| Mechanical | | | | | |
| Tensile Stress (Yield) | ISO 527-1 | 270 | kgf/cm ² | 26 | MPa |
| Tensile Strain (Break) | ISO 527-1 | >100 | % | >100 | % |
| Flexural Modulus | ISO 178 | 9,900 | kgf/cm ² | 970 | MPa |
| Impact | | | | | |
| Notched Izod Impact Strength (23 °C) | ISO 180 | 4.0 | kgf·cm/cm | 39 | J/m |
| Notched Izod Impact Strength (-10 °C) | ISO 180 | 2.5 | kgf·cm/cm | 24 | J/m |
| Thermal | | | | | |
| Heat Deflection Temperature (4.6kgf/cm ²) | ISO 75-1 | 85 | °C | | |
| Additional Properties | | | | | |
| Haze | | 25 | % | | |

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com