

Linear Low Density Polyethylene

LF20184

EVALENE® LF20184 is a medium slip, medium antiblock Linear Low Density Polyethylene grade with butene (C4) as comonomer for blown film applications.



EVALENE® LF20184 is specifically formulated for best performance in thicker films (≥ 50 microns; $\geq 0.002''$). **EVALENE® LF20184** is suitable for both the lamination and core layers in coextruded films. Films made of **EVALENE® LF20184** are notable for their toughness, flexibility and clarity - a good balance between mechanical and optical properties. The films exhibit good moisture and fair gas barrier properties, and are water resistant.

FEATURES

- Enhanced clarity
- Balanced mechanical properties
- Meets FDA Philippines food-contact requirements
- Halal certified

TYPICAL APPLICATIONS

- Flexible packaging
- Agricultural films
- Industrial liners
- Garment bags
- Trash bags
- Shopping bags
- Ice bags

Product Properties

Property	Test Condition	Test Method	Typical Value	Unit
Melt Index	190°C/2.16 kg	ASTM D1238	2.0	g/10 min
Density	23°C	ASTM D1505	0.918	g/cm ³
Tensile Strength at Yield*	500 mm/min	ASTM D882	9 / 9	MPa
Elongation at Yield*	500 mm/min	ASTM D882	51 / 21	%
Tensile Strength at Break*	500 mm/min	ASTM D882	14 / 13	MPa
Elongation at Break*	500 mm/min	ASTM D882	568 / 562	%
Tensile Modulus*	1% Secant, 25 mm/min	ASTM D882	181 / 192	MPa
Elmendorf Tear Strength*		ASTM D1922	174 / 625	g
Dart Drop Impact Strength*		ASTM D1709	61	g
% Haze*		ASTM D1003	16	%
Gloss*	45° angle of incidence	ASTM D2457	70	%
Coefficient of Friction - Static*		ASTM D1894	0.11	-
Coefficient of Friction - Kinetic*		ASTM D1894	0.09	-

*Properties tested on 25µ films made using a Killion extruder with 38mm screw, 3.5" die, 1.0mm die gap, at 2.25:1 BUR. Tensile and tear properties are in machine and transverse directions (MD / TD).

Typical Processing Conditions

Extrusion Temperatures	170 - 190°C
Blow Up Ratio	2 - 4
Die Gap	1 - 3 mm

EVALENE® LF20184 provides performance comparable to the other 2 MI, 918 Density LLDPE grade. Its mechanical properties are at par with those of the other grade's in this side-by-side evaluation. When using or switching to **EVALENE® LF20184** a converter is guaranteed ease of use and can expect similar performance.




Figure 1. Mechanical property performance of **EVALENE® LF20184** vs. other 2 MI, 918 Density LLDPE material




Figure 2. Comparison of haze between **EVALENE® LF20184** and other 2 MI, 918 Density LLDPE material




Figure 3. Comparison of gloss between **EVALENE® LF20184** and other 2 MI, 918 Density LLDPE material

EVALENE® LF20184 showcases outstanding optical properties. Its superior haze (22% lower) and gloss (18% higher) versus the other LLDPE material provide a film made of **EVALENE® LF20184** with outstanding display value.

Disclaimer:

Information provided herein is given for general purposes only. It is the customer's sole responsibility to test the product and any information provided herein to determine whether they are suitable for the customer's purposes. JGSPC MAKES NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Customers are strongly advised to review the applicable Material Safety Data Sheet before handling or using the product described herein.



Find out more about us at:
www.jgspetrochem.com