

PRODUCT DATA SHEET



LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE

Low Density Polyethylene

LF2220M

Technical support:
Polymer Technology Services
Centre
22 Pressburg Road,
Modderfontein, 1609
South Africa

Tel: +27 (0)11 458 0700
Fax: +27 (0)11 458 0734

Sales office:
Sasol Base Chemicals
PO Box 5486
Johannesburg, 2000
South Africa

Tel: +27 (0) 10 344 5000
polymers@sasol.com

Date of issue : March 2017

www.sasol.com

Melt Index: 2.0 g/10min

Density: 0.922 g/cm³

Features

- Tubular Resin
- Good clarity
- Wide sealing range
- Good drawdown

Applications

- General packaging film (20µm to 50µm)
- Clarity film
- Thin film

Additives

- Antioxidant
- Medium slip
- Medium antiblock

Typical properties (not to be construed as specifications)		Value (SI)	Value (English)	Method
Resin Properties	Melt Index (190°C/2.16kg)	2.0 g/10min	2.0 g/10min	ASTM D1238
	Nominal density	0.922 g/cm ³	0.922 g/cm ³	ASTM D1505
Film Properties	Tensile strength at yield MD	10 MPa	1450 psi	ASTM D882
	Tensile strength at yield TD	9 MPa	1305 psi	ASTM D882
	Tensile strength at break MD	21 MPa	3045 psi	ASTM D882
	Tensile strength at break TD	17 MPa	2465 psi	ASTM D882
	Elongation MD	310 %	310 %	ASTM D882
	Elongation TD	550 %	550 %	ASTM D882
	Elmendorf Tear MD	8 g/µm	8 g/µm	ASTM D1922
	Elmendorf Tear TD	6 g/µm	6 g/µm	ASTM D1922
	Dart Drop Impact Strength (F ₅₀)	65 g	65 g	ASTM D1709A
	Haze	6.5%	6.5 %	ASTM D1003
	Clarity	48	48	ASTM D1746
	Gloss (45°)	65	65	ASTM D2457
	Coefficient of friction (static)	0.1	0.1	ASTM D1894
	Coefficient of friction (dynamic)	0.1	0.1	ASTM D1894
Blocking	<25g	<25g	ASTM D3354	

The above values were measured on a 30 µm film produced on a 65 mm Macchi extruder with a Macchi LDPE screw and a 250 mm die, using 208°C melt temperature, 625 mm FLH and a 2.5:1 BUR and a die gap of 0.8mm.

Blown film extrusion

MELT TEMPERATURE 160 - 180°C

D	°C	4	3	2	1	H
	300					
	260					
	220					
	180					
	140					
	100					
	60					
	20					



Processing

LF2220M should be processed on a conventional LDPE extruder, but can be processed on a LLDPE extruder (wide die gap) with drawdown limitations, inferior mechanical and film shrinkage properties. Recommended screen pack: 60/100/60 BS mesh. The optimum melt temperature is 160°C – 180°C.

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polypropylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

Regulatory & Legal Compliance

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application.