

SABIC® PA6 S32

POLYAMIDE 6

DESCRIPTION

SABIC® PA S32 is a general purpose polyamide 6 resin of medium viscosity.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

TYPICAL APPLICATIONS

Barrier films, high tenacity filaments for fishing net and tyre cord.

TYPICAL PROPERTY VALUES

Revision 20211215

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL PROPERTIES			
Water absorption (23°C-sat)	11.1	%	ISO 62
Water Content			
Water content	≤0.06	% w/w	ASTM D6869
Extractable Content			
Extractable Content	≤0.5	% w/w	SABIC method
PROPERTIES			
Viscosity			
Relative Viscosity	3.2	-	ISO 307
POLYMER PROPERTIES			
Density			
Density	1.12	g/cm ³	ASTM D792
MECHANICAL PROPERTIES			
Rockwell Hardness			
R scale	119	-	ASTM D785
Tensile strength			
@ Yield	80	MPa	ASTM D638
Tensile Elongation			
@ Yield	4	%	ASTM D638
@ Break	87	%	ASTM D638
Tensile modulus			
Tensile modulus	2750	MPa	ASTM D638
Flexural strength			
Flexural strength	104	MPa	ASTM D790
Flexural Modulus			
Flexural Modulus	2650	MPa	ASTM D790
Izod Impact Strength			
Notched, 23°C	6	kJ/m ²	ASTM D256
THERMAL PROPERTIES			
Heat deflection temperature			
@ 1.80 MPa	57	°C	ASTM D648

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melting Temperature			
Melting Temperature	220	°C	ASTM D3418

PROCESSING CONDITIONS

Extrusion Temperature: 240°C-300°C

STORAGE AND HANDLING

Polyamide resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. In case material picks up moisture, customer is strongly advised to dry the resin prior to use. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process Polyamide resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.



STAVIAN®
CHEMICAL