

HOPELEN SFR-171H

PP HOMOPOLYMER

General Information

Description

SFR-171H is a high melt flow rate resin with a very narrow molecular weight distribution homopolymer.

It is suitable for woven & nonwoven application including spunbond as well as continuous filament yarn. Typical applications are HTY and spunbond nonwoven.

It is formulated with an anti-gasfading stabilisation package

Applications

- ◆ SPUNBOND, Continuous filament.

Physical Properties¹

Physical	Test Method	Nominal Values			
Melt Flow Index	ASTM D1238	34	g/10min		
Density	ASTM D792	0.90	g/cm ³		
Mechanical					
Tensile Stress (Yield)	ASTM D638	350	kgf/cm ²	34	MPa
Tensile Strain (Break)	ASTM D638	>100	%	>100	%
Flexural Modulus	ASTM D790	15,000	kgf/cm ²	1,460	MPa
Rockwell Hardness	ASTM D785	105	R		
Impact					
Notched Izod Impact Strength (23℃)	ASTM D256	2.0	kgf-cm/cm	20	J/m
Thermal					
Heat Deflection Temperature (4.6kgf/cm ²)	ASTM D648	109	℃		
VICAT Softening Point	ASTM D1525	152	℃		

NOTE

ISO 9001, 14001

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com