

## Diapolyacrylate Acrypet® VH-001 Heat Stabilized PMMA

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Heat Resistant, Molded

### Material Notes:

Acrypet® is a registered trade mark of Diapolyacrylate Company Limited. Information provided by Dayson Polymers.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Diapolyacrylate-Acrypet-VH-001-Heat-Stabilized-PMMA.php](http://www.lookpolymers.com/polymer_Diapolyacrylate-Acrypet-VH-001-Heat-Stabilized-PMMA.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.30 %	0.30 %	24 hrs.; ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955
Melt Flow	19 g/10 min @Load 3.80 kg, Temperature 230 °C	19 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	100	100	ASTM D785
Tensile Strength at Break	72.567 MPa	10525 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Modulus of Elasticity	3.23 GPa	469 ksi	ASTM D638
Flexural Yield Strength	107.87 MPa	15645 psi	ASTM D790
Flexural Modulus	3.138 GPa	455.1 ksi	ASTM D790
Compressive Yield Strength	108 MPa	15600 psi	ASTM D695
Izod Impact, Notched	0.209 J/cm	0.391 ft-lb/in	0.250 inches; ASTM D256
Impact	125	125	cm Falling Ball Impact

Thermal Properties	Metric	English	Comments
CTE, linear	59.9 µm/m-°C @Temperature 20.0 °C	33.3 µin/in-°F @Temperature 68.0 °F	ASTM D696
Specific Heat Capacity	1.46 J/g-°C	0.349 BTU/lb-°F	
Thermal Conductivity	0.209 W/m-K	1.45 BTU-in/hr-ft <sup>2</sup> -°F	ASTM D177
Deflection Temperature at 1.8 MPa	100 °C	212 °F	ASTM D648

<small>(264 psi)</small> Thermal Properties	Metric	English	Comments
Vicat Softening Point	115 °C	239 °F	ASTM D1525; 1 kg

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542
Transmission, Visible	93 % @Thickness 3.20 mm	93 % @Thickness 0.126 in	ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

