

# XR404T

## Injection Molding

### Description

- Heat Resistance

### Applications

- Electric & Electronic Housing, Automotive Exterior Housing(Rear Lamp Housing)

Properties	Method	Unit	XR404T
<b>Physical</b>			
Specific Gravity , 23°C	ISO 1183		1.05
Mold Shrinkage , 23°C, 3.2mm , 23°C	ISO 294-4	%	0.4 ~ 0.7
Melt Volume Rate , 220°C, 10kg	ISO 1133	cm <sup>3</sup> /10min	6.5
<b>Mechanical</b>			
Tensile Strength at Yield , 23°C, 50mm/min, 4mm	ISO 527	MPa	51
Tensile Elongation at Break , 23°C, 50mm/min, 4mm	ISO 527	%, (Min)	15
Tensile Modulus , 23°C, 50mm/min, 4mm	ISO 527	MPa	2500
Flexural Strength , 23°C, 2mm/min, 4mm	ISO 178	MPa	78
Flexural Modulus , 23°C, 2mm/min, 4mm	ISO 178	MPa	2550
Izod Impact Strength , Notched, 4mm, 23°C	ISO 180/1A	kJ/m <sup>2</sup>	15
Izod Impact Strength , Notched, 4mm, -30°C	ISO 180/1A	kJ/m <sup>2</sup>	7
Charpy Impact Strength , 4mm, 23°C	ISO 179/1eA	kJ/m <sup>2</sup>	14
Charpy Impact Strength , 4mm, -30°C	ISO 179/1eA	kJ/m <sup>2</sup>	7
Rockwell Hardness , R-Scale	ISO 2039		114
<b>Thermal</b>			
HDT , Flatwise, 1.8MPa, 4mm, Unannealed	ISO 75	°C	93
HDT , Flatwise, 0.45MPa, 4mm, Unannealed	ISO 75	°C	101
HDT , Flatwise, 1.8MPa, 4mm, Annealed	ISO 75	°C	101
HDT , Flatwise, 0.45MPa, 4mm, Annealed	ISO 75	°C	106
VICAT , 50N, 50°C/h	ISO 306	°C	111
RTI , Electrical	UL 746B	°C	60
RTI , Mechanical with Impact	UL 746B	°C	60
RTI , Mechanical without Impact	UL 746B	°C	60
Flammability, 1.5mm	UL 94		HB
Flammability, 3.0mm	UL 94		HB

### Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date : 3-Nov-17 Issued Date : 5-Apr-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

# XR404T

Injection Molding

## Description

- Heat Resistance

## Applications

- Electric & Electronic Housing, Automotive Exterior Housing(Rear Lamp Housing)

## Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	80 ~ 90
Drying Time	hrs	3 ~ 4
Maximum Moisture Content	%	~ 0.07
Melt Temperature	°C	230 ~ 260
Nozzle Temperature	°C	230 ~ 240
Mold Temperature	°C	40 ~ 60
Back Pressure, Hydraulic Type	kg/cm <sup>2</sup>	10 ~ 30

## Note

Back Pressure & Measuring Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

STAVIAN<sup>®</sup>  
CHEMICAL

Updated Date : 3-Nov-17 Issued Date : 5-Apr-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.